

BAKER SEALANTS & COATINGS CO -- ZINC CHROMATE PUTTY MIL-P-8116 -- 8030-00-145-0300
===== Product Identification =====

Product ID:ZINC CHROMATE PUTTY MIL-P-8116
MSDS Date:01/01/1985
FSC:8030
NIIN:00-145-0300
MSDS Number: BDCGJ
=== Responsible Party ===
Company Name:BAKER SEALANTS & COATINGS CO
Emergency Phone Num:201-333-6986
CAGE:FO833

=== Contractor Identification ===
Company Name:BAKER SEALANTS
& COATINGS CO., INC.
Address:234 SUYDAM AVENUE
Box:B
City:JERSEY CITY
State:NJ
ZIP:07304-3306
Phone:(201) 333-6986
CAGE:FO833
Company Name:BAKER SEALANTS AND COATINGS CO
Address:234 SUYDAM AVE
Box:City:JERSEY CITY
State:NJ
ZIP:07304-3306
Country:US
Phone:201-333-6986
CAGE:34094
Company Name:STEVEN INDUSTRIES
Address:39 AVENUE C
Box:8
City:BAYONNE
State:NJ
ZIP:07002-3417
Country:US
Phone:201-437-6501
CAGE:33150

===== Composition/Information on Ingredients =====

Ingred Name:PO

LYSULFIDE RUBBER

Fraction by Wt: 57%.

Ingred Name:ZINC CHROMATE

CAS:13530-65-9

RTECS #:GB3290000

OSHA PEL:0.1 MG/M3 (CRO3)

ACGIH TLV:0.01MG/M3(CR)A1;9192

Ingred Name:ASBESTOS APPROX 16.65%. ASBESTOS IS INCORPORATED INTO RUBBER BASE MATRIX.

RTECS #:CI6375000

Ingred Name:MERCAPTO BENZYL THIAZYL DISULFIDE, MBTS

CAS:120-78-5

RTECS #:DL4550000

Ingred Name:DIPHENYL GUANIDINE, DPG

CAS:102-06-7

RTECS #:MF0875000

===== First Aid Measures =====

First Aid:EYE

: IMMED FLUSH W/WATER AT LEAST 15 MIN

===== Fire Fighting Measures =====

Flash Point:>200F,>93C

Extinguishing Media:NON-FLAMMABLE

===== Accidental Release Measures =====

Spill Release Procedures:NORMAL CLEAN UP PROCEDURES

===== Handling and Storage =====

Handling and Storage Precautions:STORE BETWEEN 40-90F. MFG STATES PROD IS STABLE & NON-FLAMMABLE PASTE, NO VOLATILES.

Other Precautions:WA

SH THOROUGHLY AFTER HANDLING

=====
===== Exposure Controls/Personal Protection =====

Ventilation:LOCAL EXHAUST, YES

Protective Gloves:IF DESIRED

Eye Protection:IF DESIRED

Supplemental Safety and Health

MBTS, DPG, & TETRAMETHYL THIURAM DISULFIDE - METHYL TUADS - COMPRISE 6% OF PROD. ZINC CHROMATE, ASBESTOS, TALC, & CALCIUM CARBONATE MAKE UP PIGMENT PORTION & ARE 37% OF PROD. HMIS TECHNICIAN ADDED ITEM NAME, ITEM MANAGER AND VENDOR FOR TECHNICAL SUPPORT REASONS.

=====
===== Physical/Chemical Properties =====

HCC:N1

Spec Gravity:1.40

Solubility in Water:NEGLIGIBLE

Appearance and Odor:HEAVY PASTE, SLIGHT GASEOUS ODOR

Percent Volatiles by Volume:0

=====
===== Stability and Reactivity Data =====

Stability Indicator/Materials to Avoid:YES

=====
===== Disposal Considerations =====

Waste Disposal Methods:DISPOSE IAW LOCAL, STATE, FED REG.

Disclaimer (provided with this information by the compiling agencies):

This information is formulated for use by elements of the Department of Defense. The United States of America in no manner whatsoever, expressly or implied, warrants this information to be accurate and disclaims all liability for its use. Any person utilizing this document should seek competent professional advice to verify and assume responsibility for the suitability of this information to their particular situation.