

DSM ENGINEERING PLACTICS -- FIBERSTRAN G-1/40 NATURAL -- 9330-01-367-9735

=====
Product Identification
=====

Product ID:FIBERSTRAN G-1/40 NATURAL

MSDS Date:01/03/1995

FSC:9330

NIIN:01-367-9735

MSDS Number: CFVYP

=== Responsible Party ===

Company Name:DSM ENGINEERING PLACTICS

Box:3333

City:EVANSVILLE

State:IN

ZIP:47732-3333

Country:US

Info Phone Num:812-435-7500

Emergency Phone Num:812-435-7500

Pre

parer's Name:RICHARD M. WENGER

CAGE:IO618

=== Contractor Identification ===

Company Name:AKZO WILSON-FIBERFIL INTERNATIONAL

Box:City:EVANSVILLE

State:IN

ZIP:47732

Country:US

Phone:812-424-3831

CAGE:27203

Company Name:DSM ENGINEERING PLASTICS

Box:3333

City:EVANSVILLE

State:IN

ZIP:47732

Country:US

Phone:812-424-3831

CAGE:IO618

=====
Composition/Information on Ingredients
=====

Ingred Name:FIBERGLASS (FIBROUS GLASS)

CAS:65997-17-3

Fraction by Wt: 40%

Other REC Limits:NONE RECOMM

ENDED
OSHA PEL:5 MG/M3 RESP DUST
ACGIH TLV:10 MG/M3 (662F,>350C
Autoignition Temp:Autoignition Temp Text:NP
Lower Limits:NA
Upper Limits:NA
Extinguishing Media:CARBON DIOXIDE, WATER, DRY CHEMICALS.
Fire Fighting Procedures:FIREFIGHTERS AND OTHERS EXPOSED TO PRODUCTS OF
COMBUSTION SHOULD WEAR SELF-CONTAINED BREATHING APPARATUS.
Unusual Fire/Explosion Hazard:NONE

===== Accidental Release Measures =====

Spill Release Procedures:SWEEP UP SPILLED MATERIAL TO PREVENT
SLIPPING
HAZARD.
Neutralizing Agent:NONE SPECIFIED BY MANUFACTURER.

===== Handling and Storage =====

Handling and Storage Precautions:STORE IN COOL DRY PLACE.KEEP CNTNRS
CLOSED TO PREVENT MOISTURE ABSORPTION &/OR CONTAMINATION.
Other Precautions:NONE.

===== Exposure Controls/Personal Protection =====

Respiratory Protection:NOT REQUIRED UNDER NORMAL PROCESSING CONDITIONS.
Ventilation:GEN MECHANICAL:ACCEPTABLE. LOCAL EXHAUST:PREFERRE
D.
Protective Gloves:RECOMMENDED WHEN HDN LG HOT CMPD
Eye Protection:SAF GLASSES RECOMMENDED WHEN HND LG CMPD
Other Protective Equipment:NONE
Work Hygienic Practices:NONE SPECIFIED BY MANUFACTURER.
Supplemental Safety and Health
FLASH POINT FOR BASE POLYMERS BY ASTM D-1929.

===== Physical/Chemical Properties =====

HCC:N1
Boiling Pt:B.P. Text:NA
Melt/Freeze Pt:M.P/F.P Text:NP
Decomp Temp:Decomp Text:NP
Vapor Pres:NA
Vapor Density:NA
Spec Gravity:NP
pH:NA
Viscosity:NP
E

vaporation Rate & Reference:NA
Solubility in Water:NEGLIGIBLE
Appearance and Odor:SOLID CYLINDRICAL PELLETS, NO SIGNIFICANT
ODOR,(DISSOLVES IN FORMIC ACID)
Percent Volatiles by Volume:NA
Corrosion Rate:NP

===== Stability and Reactivity Data =====

Stability Indicator/Materials to Avoid:YES
STRONG ACIDS & OXIDIZING AGENTS.
Stability Condition to Avoid:PROLONGED HEATING ABOVE 650F.
Hazardous Decomposition Products:CO, CO2, HCN, NH3, (NO)X.

===== Disposal Considerations =====

Waste Disposal Methods:EPA HAZ WASTE CLASS:NONE.INCINERATOR OR LANDFILL
IAW LOCAL, STATE AND FEDERAL REGULATIONS.

Disclaimer (provided with this information by the compiling agencies):
This information is formulated for use by elements of the Department
of Defense. The United States of America in no manner whatsoever,
expressly or implied, warrants this information to be accurate and
disclaims all liability for its use. Any person utiliz
ing this
document should seek competent professional advice to verify and
assume responsibility for the suitability of this information to their
particular situation.